INFORCE 65/35

Inforce65/35 is a steel fibre cold-drawn wire for reinforced concrete.

Inforce65/35 is designed in order to avoid balling issues, and to improve the durability of the concrete.

Inforce65/35 can replace all conventional reinforcing methods for concrete or can be used in combination with them.



Collated 0.54 mm (0.021 inch)



KEY BENEFITS

- Increase load bearing capacity.
- Control shrinkage cracks.
- Improve durability.
- Reinforce the concrete multi-directionally.
- Reduce construction time.

TECHNICAL INFORMATION

PROPERTIES

Compliance	ASTM A 820/A820M ASTM C1116/C1116M EN 14889-1	
Tensile Strength (Rm)	1,250 N/mm² (181,300 psi)	
Young's Modulus	210,000 N/mm (30,457,900 psi)	

DIMENSIONS

Length	Equiv.	Aspect	Quantity
	Diam.	Ratio I/D	of fibers
35 mm	0.54 mm	65	15,105 fibers/kg
(1.38 inch)	(0.021 inch)		(6,852 fibers/lb)

CERTIFICATES

Inforce65/35 fibres are certified to CE mark and structural use (system 1) according to European Standard.

Manufactured under ISO 9001 and ISO14001 certification.

PACKING

- 20kg (44lb) paper bag
- 1000kg (2200lb) big bag

SAFETY

 We recommend that gloves and eye protection be used when handling fibre.

STORAGE

Store in a dry area.

APPLICATIONS

- Mining
- Shotcrete
- Slope stabilisation
- Precast concrete product
- Cast in place concrete
- Industrial slab and floor
- Commercial floor
- Concrete pavement























